## DuPont™ Tyvek® Housewrap **Technical Datasheet**



Application: Flexible sheets for water proofing - Part 2: Underlays for walls EN 13859-2: 2010

1060B Style name Language English **HDPE** Type of carrier Applicable for UK, Ireland

PROPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
FUNCTIONALITY: WA	TER VAPOUR TRANSMISSI	ON, WATER TIGHTNI	ESS, WEATHER DURA	BILITY, FIRE CLASS	
Nater vapour transmission (sd)	EN ISO 12572 (C)	m	0,01	0,003	0,025
emperature resistance	-	°C	-	-40	+100
lexibility at low temperature	EN 1109	°C	-	-	-40
IV exposure	-	months	-	-	4
roduct- / Functional layer thickness	-	mm	0,185 / 0,185	-	-
Vater tightness	EN 1928 (A)	class	W1	-	-
Vater column	EN 20811	m	1,6	-	-
eaction to fire	EN ISO 11925-2	class	E (*)	-	-
	PHYSICAL AND	MECHANICAL PROF	PERTIES		
lass per unit area	EN 1849-2	g/m²	61	58,5	63,5
Maximum tensile force (MD)	EN 12311-1	N/50mm	310	280	340
longation at max. tensile force (MD)	EN 12311-1	%	17,5	15	20
Maximum tensile force (XD)	EN 12311-1	N/50mm	310	270	350
longation at max. tensile force (XD)	EN 12311-1	%	20	16	24
lesistance to tearing MD (nail shank)	EN 12310-1	N	50	37	65
desistance to tearing XD (nail shank)	EN 12310-1	N	45	32	60
	PROPER	RTIES AFTER AGEING			
rtificial ageing by UV and heat:	EN 1297 & EN 1296	residual value			
Water tightness	EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)	EN 12311-1	%	80	-	-
MD elongation at max. tensile force	EN 12311-1	%	70	-	-
Maximum tensile force (XD)	EN 12311-1	%	80	-	-
XD elongation at max. tensile force	EN 12311-1	%	70	-	-
	ADDITI	ONAL PROPERTIES			
ength (customer related, expressed in m)	EN 1848-2	deviation in %	0	0	-
/idth (customer related, expressed in mm)	EN 1848-2	deviation in %	0	-0,5	+1,5
traightness	EN 1848-2	mm/10m	-	-	30
rimensional stability (MD & XD)	EN 1107-2	%	-	-	1
esistance to penetration of air	EN 12114	m³/(m² h 50Pa)	-	-	2
Vindtight	-	-	yes	-	-

The product mentioned above, in our opinion, fulfils the criteria of being classified as 'article' (REACH, Art. 3.3). There are no substances intended to be released from this product under normal or reasonably foreseeable conditions of use. The above article to our current knowledge does not contain substances, above the legal threshold, that are on the 'Candidate List' of Substances of Very High Concern (SVHC) as published on the ECHA website.



DuPont (UK) Limited HERE, 470 Bath Road, Arnos Vale, Bristol , BS4 3AP

tyvek.construction@dupont.com Tel +44 (0) 117 452 9050

www.building.dupont.co.uk

Effective date: 15/12/2023 First CE: 23/11/2005



Some test methods are modified according to the EN 13859-2-2010 and/or according to the DuPont ISO 9001:2015 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of or application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.